

since **1875**

TECHNICAL SHEET 14.07.01-EN



JUBIN Polyurethane varnish

Thick-coat transparent polyurethane lacquer (gloss, matt)

1. Description, Application

JUBIN Polyurethane varnish is a transparent coating for wood, made on the basis of a water dispersion of acrylic - polyurethane binders, without an unpleasant smell, easy to apply and dries quickly. It is intended for the decorative and mechanical protection of interior wooden surfaces, such as ceiling and wall coverings, solid wood furniture, and other miscellaneous objects made of all types of wood. The dry coating film enhances the look of the wood and preserves the visible structure.

2. Colour Shades

Transparent

3. Technical data

Packaging		0.65 I, 2.25 I
Density		~1.018 kg/dm³
Content of vaporous substance (VOC)		11 g/l
The EU VOC requirement - category		A/e<
Water dilution mass		0 %
Water dilution for spraying		~10 %
Drying time	Touch dry	~2 h
T = +20 °C, relative air humidity = 65 %	Suitable for further treatment	~4-6 h
Consumption		~100 - 140 ml/m²
Recommended number of layers		2-3
Gloss level	Gloss	86 GU/60°



Matt

14 GU/60°

4. Installation Conditions

The air temperature should not be lower than $+5^{\circ}$ C and not higher than $+30^{\circ}$ C (the optimum air temperature is $+10^{\circ}$ C to $+25^{\circ}$ C), and the air humidity should not exceed 80 %.

5. Surface Preparation

Surface should be solid, dry and clean, without any badly-adhered particles, dust, fat linings or other filth. Wood humidity should not exceed 12 % (deciduous trees) or 15 % (coniferous trees). Clean resinous surfaces of wood with nitro diluter and let them dry well. Repair any defects (cracks, dents, hollows and similar) with JUBIN Akrilin wood paste (apply the paste in the shade closest to the colour of wood).

If the surface of the wood is very smooth, sand it with fine sandpaper or a sanding sponge. If the coating is used on surfaces where old coatings are present, remove them mechanically and thoroughly sand and clean the surface of dust.

6. Preparation of coating

Prior to application, only stir JUBIN Polyurethane varnish well. In case of application by spraying (in conditions of accelerated drying as well as in other cases), it can be diluted, but not more than 10 %.

7. Application of coating

JUBIN Polyurethane varnish is applied in two or three layers to a dry and clean surface with a brush, a suitable paint roller (velour 2 mm) or by spraying. Due to quick drying, application in stripes without interruptions is recommended. Smear any drops immediately so that they do not dry. Before the second application, gently sand the coated surface with fine sandpaper to remove raised wood fibers.

For spraying with an air gun, we recommend using a nozzle of 1.2 to 1.5 mm, an air pressure of 3 to 4 bar.

Immediately after use thoroughly clean the tools with water or water solution of universal household detergents.

8. Maintenance and Restoration of Painted Surfaces

Surfaces treated with JUBIN Polyurethane varnish do not require special maintenance. If recoating is needed, just sand the surfaces with fine sandpaper or a fine sanding sponge, or see section "5. Preparation of the base".

9. Storage, Transportation Conditions and Durability

Storage and transport at temperature between +5 °C and +25 °C, keep out of direct sunlight, out of reach of children, MUST NOT FREEZE!

Shelf life when stored in an originally sealed and undamaged packaging: at least 18 months.

10. Other Information

Technical instructions contained in this brochure are provided on the basis of JUB's experience and are given as a guideline to achieve the optimum results. JUB cannot accept any responsibility for damage caused by incorrect selection of a product, incorrect use or unprofessional work.

Safety measures: Follow the instructions on the safety data sheet of the product.

The colour shade may differ from the print in the colour chart since it depends on the type and absorption of wood, roughness of the surface and the number of applications. In order to check the colour shade, a dry application of the coating on a standard test cardboard is compared to a standard of the concerned shade, which is stored in the TRC JUB d.o.o. A difference in the colour shade, which is the result of unsuitable working conditions, of coat preparation technique, which differs from the one in this technical sheet, of the application of the product onto an unsuitably prepared surface and on a wet or not dried enough surface, cannot be subject of complaint.



This technical sheet supplements and replaces all preceding editions. JUB reserves the right to change and supplement data in the future.

Designation and date of issue: TRC-072/21-čad, 02.08.2024

JUB d.o.o. Dol pri Ljubljani 28, 1262 Dol pri Ljubljani, Slovenija T: 01 588 41 00 (h.c.), 01 588 42 17 (prodaja), 01 588 42 18 ali 080 15 56 svetovanje E: jub.info@jub.si jub.eu



